

Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date:

24 November 2023

Our Ref:

23/61574A/11/23

Your Ref:

__

Page:

1 of 5

Client:

Solarglide Ltd

Unit H, the Stottie Shed 5 Bakers Yard Christon Road Newcastle Upon Tyne

NE3 1XD

Job Title:

Fire Test on One Roller Blind Sample

Clients Order Ref:

Date of Receipt:

16 November 2023

Date Test Started:

23 November 2023

Description of Sample:

One sample of roller blind, which was referenced by the client as;

IONA Dimout Fabric - Charcoal

Work Requested:

We were asked to make the following fire test:

IMO FTP Code 2010:Part 7

- subcontracted test, UKAS accredited
- ** subcontracted test, EN ISO/IEC 17025 accredited
- *** not UKAS accredited





Note: This report relates only to the items tested.



Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date:

24 November 2023

Our Ref:

23/61574A/11/23

Your Ref:

Page:

2 of 5

Client:

Solarglide Ltd

Product Description

| Company Name | Solarglide Limited | | | |
|---|----------------------------------|--|--|--|
| Type of Material, i.e. Curtain, Drape, etc. | Roller Blind Fabric | | | |
| Name and/or Identification of the Product Tested | IONA Dimout Fabric | | | |
| Mass per Unit Area (g/m²) | 290g/m² (8.55oz/yd²) | | | |
| Thickness (mm) | 0.5mm (estimate) | | | |
| Colour and Tone (i) | Charcoal | | | |
| Quantity and Number of Any Coating | No specified - no backing lining | | | |
| Method and Quantity of Fire-Retardant Treatment | BS 5867 Part 2 Type B | | | |
| Materials of the Product and its Composite Ratio (ii) | 100% Polyester - plain fabric | | | |
| Composition of Weave (iii) | 100% Polyester - plain fabric | | | |
| Density (Number/Inch) the Number of Threads per Inch in both warp and weft; and | Not specified | | | |
| Yarn Number Count | Not specified | | | |

- (i) If the product has a pattern, the representative colour shall be described.
- (ii) Such as wool, nylon, polyester, etc.
- (iii) Such as plain, weave, twilled.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 24 November 2023

Our Ref: 23/61574A/11/23

Your Ref:

Page: 3 of 5

Client:

Solarglide Ltd

FIRE TESTS ACCORDING to IMO FTP Code 2010:Part 7 Test for Vertically Supported Textiles and Films

Cleaning Procedure

The sample received no pre-treatment as the fabric was stated to be inherently flame retardant.

Conditioning

The sample was conditioned for not less than 24 hours in the standard atmosphere for conditioning textiles of $20\pm\,5^{\circ}\text{C}$ and $65\pm\,5\%$ R.H.

Procedure

The sample was tested in accordance with IMO FTP Code 2010:Part 7*. The sponsor sampled the material and the specimens were cut from the sample received to the dimensions set out in the standard.

A 40mm high propane gas flame was applied to the edge of 5 warp and 5 weft specimens for 15 seconds.

The after-flame time, length of char, existence of surface flashing and ignition of cotton waste from drops were recorded.

*Deviation from standard

The test was carried out in a test enclosure to different dimensions to that specified in IMO FTP Code 2010:Part 7. The dimensions of the test enclosure are 1820mm wide x 1220mm deep x 1950mm. The test was carried out in a draught free enclosure.







Telephone: +44 (0) 113 259 1999 Email: onestopshop@bttg.co.uk

Website: www.bttg.co.uk

Date: 24 November 2023

23/61574A/11/23 Our Ref:

Your Ref:

Page: 4 of 5

Client:

Solarglide Ltd

Requirements

The Performance Criteria for Curtains and Drapes states that: Products which show any of the following characteristics obtained by the fire test in appendix 1, shall be considered unsuitable for use as curtains, drapes or free-hanging fabric product for use in rooms containing furniture and furnishings of restricted fire risk as defined in the relevant regulations of chapter II-2 of the Convention:-.

- An after-flame time greater than 5 sec for any of the 10 or more specimens tested with surface application of the 1.
- Burn through to any edge of any of the 10 or more specimens tested with surface application of the pilot flame. 2.
- Ignition of cotton wool below specimen in any of the 10 or more specimens tested. 3.
- An average char length in excess of 150mm observed in any of the 10 or more specimens tested by either surface or edge ignition.
- The occurrence of a surface flash propagating more than 100mm from the point of ignition with or without charring 5. of the base fabric.

If it is found that either or both of the batches of five specimens cut in both warp and weft directions fail to meet one or more of the criteria specified in subparagraphs .1 to .3 and .5 above because of poor performance of only one of the five specimens tested, one complete retest of a similar batch is permitted. Failure of the second batch to meet any of the criteria shall provide the basis for rejection of the fabric for use.

Results

| | After flame time (s) | | 9 | | Flaming to edge (yes or No) | | Ignition of Cotton Wool from Flaming Drops (Yes or No) | | Surface Flashing (Yes or No), if yes, Propagation Length (mm) | |
|------|----------------------|------|------|------|--------------------------------|------|--|------|--|------|
| | Warp | Weft | Warp | Warp | Weft | Weft | Warp | Weft | Warp | Weft |
| | 0 | 0 | 91 | 100 | No | No | No | No | No | No |
| | 0 | 0 | 90 | 95 | No | No | No | No | No | No |
| | 0 | 0 | 99 | 94 | No | No | No | No | No | No |
| | 0 | 0 | 96 | 98 | No | No | No | No | No | No |
| | 0 | 0 | 97 | 90 | No | No | No | No | No | No |
| Mean | 0 | 0 | 95 | 95 | | | | | | |



